

COMPATIBILITY CHART ANTIFOULING Sea-Line®

CURRENT COAT ANTIFOULING		NEW ANTIFOULING PAINT SEA-LINE®		
		• **SELF-POLISHING** • **ALU PLUS Self-polishing** • **POLISHING - Silver Cruise** • **SEGUARD Fouling Stop**	• **HARD ANTIFOULING** • **HARD - Silver Speed**	• **THIN FILM - Silver Racing**
SEA-LINE®	▪ SELF-POLISHING ▪ ALU PLUS SELF-POLISHING ▪ POLISHING – Silver Cruise ▪ SEAGUARD			
	▪ HARD antifouling ▪ HARD - Silver Speed			
	▪ THIN FILM - Silver Racing			
OLD ANTIFOULING	▪ Unknown product in good condition (with the exception of Teflon paints)			
	▪ Self- polishing antifouling in good condition			
	▪ Hard antifouling in good condition			
	▪ Antifouling type THIN FILM in good condition			
	▪ Hard antifouling with PTFE in good condition			
	▪ Previous antifoulingu in poor condition			

Do not risk! If existing antifouling coat is in bad condition, remove it !

Basic recommendation for surface preparation and paint application Sea-Line® :

- **Use biocides safely. Always read the label and product information before use**
- When using the product in a small, enclosed space you must provide forced ventilation
- Avoid contact of liquid with eyes and skin
- Please follow safety instructions from the technical data sheet for hazardous chemical and follow workplace safety laws

	• Clean old surface with water under pressure (remove splinters and repair damage on the surface) • places after repair or grinded surfaces from antifouling paint protect using 1K UNIVERSAL PRIMER Sea-Line® • Apply 1-3 layers of Sea-Line antifouling
	• Clean old surface with water under pressure (remove splinters and repair damage on the surface) • Abrade P100-P240 all surface • places after repair or grinded surfaces from antifouling paint protect using 1K UNIVERSAL PRIMER Sea-Line® • Apply 1-3 layers of Sea-Line antifouling
	• Clean old surface with water under pressure (remove splinters and repair damage on the surface) • Abrade P100-P240 all surface • Apply a barrier coat of 1K UNIVERSAL PRIMER Sea-Line® • Apply 1-3 layers of Sea-Line antifouling
	• Remove all layers of old antifouling P100-P240 all surface • Apply minimum 1 layer primer: ▪ 2K Epoxy Lightprimer 5:1 Sea-Line® - laminates (GRP) ▪ 2K Epoxy Anticorrosive 4:1 Sea-Line® - steel, aluminium ▪ 2K Epoxy Woodprimer 10:4 Sea-Line® - wood ▪ 1K UNIVERSAL PRIMER Sea-Line® - laminates, steel, wood, • Apply by 1-3 of layers Sea-Line antifouling